

UHU® SPRAY ADHESIVE

CONTACT SPRAY ADHESIVE



PRODUCT DESCRIPTION

UHU Spray Adhesive – the spray contact adhesive for small and large surfaces. Glues fast, strong and clean various materials, also suitable for Styrofoam®. Extra smooth and even spray pattern – no bleed-through of the adhesive, even through thin materials. It also enables an economical usage. Non-clog spray valve.

FIELD OF APPLICATION

For permanently or temporarily bonding paper, cardboard, photos, posters, reproductions, collages, metal foils (aluminium foil) and for the temporary fixation of stencil plates. Also suitable for gluing insulation and decorative materials, such as polyether foam/foam rubber (sound insulation, furniture cushions), felt, textile, leather, cork, polystyrene foam (tempex), to themselves as well as to wood, board, chipboard, glass, concrete and metals. Not suitable for PE, PP.

PROPERTIES

- For temporary and permanent fixation
- Easy to use
- Fast and strong
- Moisture resistant

PREPARATION

Working conditions: Do not use at temperatures below +10 °C.

Personal safety: Spray adhesive contains volatile, highly flammable solvents. Appropriate precautions should be taken when using and storing this product. When applying product to larger surfaces, ensure good ventilation in the working area.

Surface requirements: The areas to be glued must be dry and free of any dust or grease.

APPLICATION

Coverage: 5 m²/l, applied on both sides

Directions for use:

Shake aerosol spray can well prior to use.

Rock solid bond: Immediate fixation: Apply adhesive to both sides. Allow to dry for at least 10 minutes, join parts and press or tap. No adjustments possible. **Adjustable fixation:** It is also possible to apply adhesive to one side and join the parts immediately. Adjustments are possible within 5 minutes, approx. drying time 24 hours.

Reusable bond: Apply adhesive to one side (not the substrate). Allow to dry for at least 20 minutes, join parts and press well. The bonded object is now self-adhesive and can be removed and fixed again.

After spraying, hold can upside down and press spray head until only propellant and no more adhesive comes out. This prevents clogging up of spray can.

Stains/residue: Remove fresh stains immediately with benzene. Let dried stains soak in benzene.

Points of attention: Pressurized container. Protect from sunlight and do not expose to temperatures exceeding 50°C. Do not pierce or burn, even after use. Throw away only when completely empty. Do not breathe vapour. Do not spray on a naked flame or any incandescent material. Keep away from sources of ignition – Do not smoke. Without adequate ventilation accumulation of potentially explosive alloys possible. Keep out of reach of children.

CURE TIMES*

Drying/Curing time: approx. 10 minutes for permanent bonding and approx. 20 minutes for temporary fixation.

* Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

TECHNICAL PROPERTIES

Moisture resistance: Good

Temperature resistance: -40°C to +50°C

Chemicals resistance: Good

TECHNICAL SPECIFICATIONS

Chemical base: SBR - Rubber

Colour: Transparent

Viscosity: approx. Liquid

Solid matter: approx. 22 %

Density: approx. 0.72 g/cm³

STORAGE CONDITIONS

At least 24 months after date of manufacture. Limited shelf life after opening. Store in a dry, cool and frost free place.