

UHU® WOOD GLUE

HIGH QUALITY, MOISTURE RESISTANT (EN 204 D2) WHITE WOOD GLUE.



PRODUCT DESCRIPTION

High quality, moisture resistant (EN 204 D2) white wood glue for indoor use. Dries transparent. Stronger than wood. For bonding and laminating of practically all hard, soft and exotic types of wood.

FIELD OF APPLICATION

For moisture resistant bonding and laminating of practically all hard, soft and exotic types of wood. Suitable for well-fitting, non-load bearing wooden structures using, for example, finger joints, dovetail joints, mortise and tenon joints, dowels and springs. Suitable for indoor applications such as doors and furniture in, for example, living rooms and offices. For surface bonding wood, hard and softboard, chipboard, multiplex plywood, MDF, paper, cardboard and hardboard. Also suitable for laminating veneer and hard plastic sheet (HPL, Formica, Duroopal, Resopal) on a wooden surface. EN 204 D2: Interior spaces in which increased relative humidity occurs occasionally and for a short time, whereby the level of wood humidity remains below 18%.

PROPERTIES

- Stronger than wood
- Transparent when dry
- Ideal for internal applications
- Paintable
- Solvent-free

PREPARATION

Working conditions: The ambient temperature, the adhesive and the materials to be bonded should be no less than +5°C. Relative humidity of up to 65%. Level of wood humidity between 8% and 12%.

Surface requirements: The surfaces to be bonded need to be clean, dry and free of dust. Ensure a well-fitting joint.

Preliminary surface treatment: Degrease oily types of wood with thinner.

Tools: Fine-toothed glue spreader (1 mm), brush or roller, clamp or press.

APPLICATION

Dilute: If necessary, dilute with water to the original viscosity.

Coverage: 2-4 m²/kg, applied on both sides, depending on the nature of the materials.

Directions for use:

Apply the adhesive with a brush or some other tool in an even and thin layer on one or both parts. Let penetrate for a few minutes, then assemble the parts and clamp or press for 1-2 hours. The desired pressure is 2-5 kg/cm².

Pressure: 5-10 kg/cm²

Time to press (+20°C): 15 minutes (more in case of tension)

Open time: 8 minutes

Stains/residue: Remove adhesive residues immediately with water. Dry adhesive residue can only be removed mechanically.

Advice: For water resistant bonding, use UHU Wood Glue Exterior (EN 204 D3).

TECHNICAL PROPERTIES

Moisture resistance: Good

Water resistance: Limited

Temperature resistance: -20°C - +60°C

Paintability: Good

Filling capacity: Nil

TECHNICAL SPECIFICATIONS

Chemical base: Polyvinyl acetate dispersion

Colour: White (Transparent when dry)

Viscosity: approx. 12.000 mPa.s., Liquid

Solid matter: approx. 50 %

Density: approx. 1.1 g/cm³

White point: approx. 3 °C

pH-value: approx. 7

Flash point: K3 (>55°C)

STORAGE CONDITIONS

At least 24 months after date of manufacture. Limited shelf life after opening.

Close container properly and store in a dry, cool and frost-free place.