

UHU® PORCELAIN

SEMI-FLUID WHITE REPAIR ADHESIVE



Chemicals resistance: Good

Paintability: Good

TECHNICAL SPECIFICATIONS

Appearance: White liquid

Chemical base: Synthetic Nitro Resins

Bonding technique: 2-sided application

Colour: White

Consistency: Medium viscosity

Viscosity: approx. Liquid

Solid matter: approx. 52 %

Density: approx. 0.95 g/cm³

Specifications: Flame point [°C]: +21

STORAGE CONDITIONS

Store the product in a cool but frost-free place!

PHYSIOLOGICAL PROPERTIES

The dried adhesive is inert, completely neutral and physiologically indifferent.

PACK SIZES

tube: 13ml/ 13g

PRODUCT DESCRIPTION

Semi-fluid white repair adhesive for gluing, sealing and repairing porcelain, marble, stoneware and ceramics.

PROPERTIES

· may be diluted with acetone

PREPARATION

Personal safety: UHU Porcelain contains volatile, highly flammable solvents; precautions are therefore necessary during use and storage. Ensure proper ventilation when using over large areas.

Surface requirements: Surfaces that are to be repaired must be clean, dry and free of oil, grease and dust.

APPLICATION

Dilute: Light petrol

Directions for use:

Apply UHU Porcelain to both sides of fracture and leave to dry. Then apply another coat of adhesive to one side and press parts together immediately. Items such as crockery should be rinsed in hot water before use.

Stains/residue: Specks can be removed with acetone.

CURE TIMES*

Final bonding strength after: approx. 24 hours

* Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

TECHNICAL PROPERTIES

Water resistance: Good

Temperature resistance: +80°

Note: This information is the result of carefully executed tests. This Technical Data Sheet has been prepared to the best of our knowledge to provide you with advice when gluing. We cannot be held responsible for the results or any damage suffered, as the variety of factors involved (type and combination of materials and working method) are beyond our control. Users have to carry out their own checks and trials. Liability can only be accepted for the consistently high quality of our product.