



WOOD MAX POWER

EXTRA STRONG, WATERPROOF, DI-ISOCYANATE FREE, SMP WOOD CONSTRUCTION ADHESIVE



PRODUCT DESCRIPTION

Extremely strong, waterproof, di-isocyanate free and filling wood construction adhesive based on SMP-Polymer.

FIELD OF APPLICATION

For waterproof (D4) (surface) bonding of practically all types of wood as well as bonding practically all types of wood to many building materials, such as gypsum, (natural) stone, (cellular) concrete, metal, hard foam and various synthetics. Suitable for non-load bearing wooden structures using various wood joints such as mortise and tenon joints, dowels and springs. Suitable for interior and exterior applications, such as façade carpentry and sandwich panels. Very suitable for less-fitting joints (for example, unplanned wood). Ideal for both vertical and horizontal applications. D4: Interiors where flowing water or condensation are present over long periods on a regular basis. Exteriors exposed to the influences of the weather, providing effective protection for bonded wood.

Not suitable for PE (polyethylene), PP (polypropylene) and PTFE

PROPERTIES

- Extremely high final bond strength (110 kg/cm²)
- Waterproof (D4)
- PU & Solvent free
- Very good filling capacity (up to 4 mm)
- Can be scraped immediately
- Permanently flexible
- Paintable
- All-weather resistant
- UV resistant
- Thixotropic
- Good standing power; does not drip

- Innovative formula: patented formula

CERTIFICATES & STANDARDS

Standards	
EN 204 D4	EN 204: Classification of thermoplastic wood adhesives for non-structural applications: D4

PREPARATION

Working Conditions: The ambient temperature, the adhesive and the materials to be bonded should not be less than +5°C. Wood humidity must preferably be between 10% and 18% (max. 25%).

Surface Requirements: Surfaces must be clean, dust- and grease-free.

Preliminary Surface Treatment: Degrease oily types of wood. Roughen non-porous materials.

Tools: Fine-toothed glue spreader (1 mm), brush, roller, clamp or press.

APPLICATION

Coverage: With spot bonding: 5-8 m²/kg.

Directions for use:

Apply the adhesive evenly directly from tube on one or both sides (depending on application). Where needed spread further with sealant gun, glue spreader, brush or roller. Ensure adequate layer thickness. Assemble joint within 30 minutes and fixate for at least 6 hours. Pressing or clamping is not necessary. If pressed or clamped, use a limited pressure to avoid too much adhesive to be pushed out of the bond.

Stains/residue: Remove wet adhesive residue immediately. Dry adhesive residue can only be removed mechanically.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



WOOD MAX POWER

EXTRA STRONG, WATERPROOF, DI-ISOCYANATE FREE, SMP WOOD CONSTRUCTION ADHESIVE

TECHNICAL SPECIFICATIONS

Chemical base:	SMP Polymer
Chemicals resistance:	Good
Colour:	Beige (mixture)
Cure rate:	1 mm/24h
Density approx.:	1.34 g/cm ³
Elasticity:	Nil
Filling capacity:	Very good
Final bond strength:	1100 N/cm ²
Final bond strength after:	24 hours. This might vary, based on circumstances, like materials, temperature and humidity.
Hardness (Shore A):	95
Initial Bonding after:	6 hours. This might vary, based on circumstances, like materials, temperature and humidity.
Initial bond strength:	100 N/cm ²
Minimum temperature resistance:	-40 °C
Maximum temperature resistance:	120 °C
Moisture resistance:	Very good
Paintability:	Very good
Shear strength:	1100 N/cm ²
Shrinkage approx.:	0 %
Skinover time:	30 minutes
Solid matter approx.:	100 %
UV resistance:	Good
Viscosity:	Thixotropic
Water resistance:	Very good
Wood glue classification:	D4

STORAGE CONDITIONS

Store in properly sealed packaging in a dry place at between +5°C and +25°C.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.